



Easy Clean Coating

for ceramic sanitary ware,
shower glass and glazed wall tile

**PRODUCT,
APPLICATION
AND
SPECIFICATION
MANUAL**





Easy Clean Coatings

**PRODUCT,
APPLICATION
AND
SPECIFICATION
MANUAL**

Contents

Product Bulletins

- [Easy Clean Coating ECC-1000](#)
- [Easy Clean Coating ECC-4000](#)
- [Easy Clean Coating ECC-5000](#)

Application Guidelines

- [General Application Notes](#)
- [ECC-1000 for Ceramic Substrates](#)
- [ECC-4000 for Ceramic and Glass Substrates](#)
- [ECC-5000 for Glazed Ceramic Wall Tiles](#)

Test Methods

- [Measurement of static contact angle](#)
- [Abrasion test with water](#)
- [Abrasion test with cleaner](#)
- [Exposure test to HCl](#)

Performance Recommendations

- [Ceramic sanitary ware](#)
- [Glass for shower cabins](#)
- [Glazed wall tiles](#)

Scotchgard™ Protector Performance Specifications

- [Ceramic Sanitary Ware Shower Glass](#)
- [Ceramic Wall Tile](#)

Quality Monitoring Requirements

- [Quality Monitoring Requirements](#)

*For the most current version of any 3M MSDS, please refer to the 3M MSDS Search Tool at <http://www3.3m.com/search/w/en001/msdssearchform.do>



Easy Clean Coating ECC-1000

For Ceramic Substrates

Introduction 3M™ Easy Clean Coating ECC-1000 is a clear, colorless treatment for ceramic sanitary materials that can be used to provide “Easy to Clean” surfaces. This fluoropolymer will react with the surface to create a low surface energy coating that is not easily wetted out with liquids. The treatment is stable and cannot be removed except by harsh cleaners or reagents, such as a very strong base.

This product is typically applied from a very diluted solution containing about 0.1% by weight of product, resulting in coating thickness of 20 to 100 nm. ECC-1000 coating can be applied by spray application or dip coating. The treatment provides a hydrophobic surface that allows simple rinsing away of soils and sludge from the surface with no residual surface staining. The treated surface is durable, highly repellent to oils and water and does not change surface appearance.

Application ECC-1000 coating can be applied to ceramics and other siliceous or silicate surfaces to provide low surface energy benefits. Application is usually performed at the OEM level.

The treated substrate will have:

- 1. Surface protection** ECC-1000 coating can be used for ceramic materials such as sinks, toilets, showers tubs and other sanitary fixtures.
- 2. Oil- and water-repellency** ECC-1000 coating will provide repellency against any liquid having a surface tension greater than about 15 dynes/cm. This includes water, oils, ketones, and aromatic and aliphatic hydrocarbons.
- 3. Easy-to-clean properties** ECC 1000 coating is a built-in, manufacturer applied treatment that provides an easy to clean surface, resulting in consumer advantages such as:
 - resists stains
 - easy to remove hard water deposits
 - no need for aggressive cleanersNote: “Easy-to-Clean” does not mean the surface is “self-cleaning.”
- 4. Enhanced lubricity** Soils and liquids tend to “slide off” surfaces treated with ECC-1000 coating, helping to prevent build-up and extend the time between cleanings.

3M™ Easy Clean Coating ECC-1000 Typical Physical Properties

Not for
specification
purposes

All values
determined at
25°C and 1
atmosphere
unless otherwise
specified

ECC-1000 coating can be described as a 100% liquid fluoropolymer.

Properties	ECC-1000 Coating
Appearance	Slightly viscous, slightly yellow liquid
Specific gravity	1.6 kg/l
Flash Point	none
Type	non-ionic
Composition	100% fluoropolymer

ECC-1000 coating can be diluted with alcohols, ketones, acetates or other solvents to give slightly hazy mixtures.

ECC-1000 coating can be diluted with hydrofluoroethers (HFE) to give clear solutions. Instructions for proper product application can be found in the Application Guidelines.

Typical Performance Data	ECC-1000 Coating
Initial contact angles (water/hexadecane)	90°-105°/55°-65°
Contact angles after abrasion 50,000 cycles with WC-eend* cleaner 40 cycles with Cif**	80°-95°/45°-50° 70°-80°/40°-45°
Contact angles after exposure 24 hrs 18% HCl at 20°C	90°-95°/50°-55°

* "WC-eend cleaner" is a trademark of Bolton Group

** "Cif" is a trademark of Lever Fabergé

Storage and Shelf Life

It is recommended that ECC-1000 coating be stored in a closed bottle, away from direct sunlight, in a cool, dry place (temperatures between 10-25°C/50°-70°F). Avoid contact with moisture. Shelf life is 1.5 years from date of 3M manufacture.

Product Safety and Handling

Before using this product, please read the Material Safety Data Sheet (available through your local 3M representative) and the precautionary information and directions for use on product packaging. Follow all applicable precautions and directions for use.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

Asia Pacific and Latin America

Call (U.S.) 651 736 7123

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.



3M Specialty Materials

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3737-9



Easy Clean Coating ECC-4000

For Ceramic and Glass Substrates

Introduction 3M™ Easy Clean Coating ECC-4000 is an air-dried, clear, colorless treatment for ceramic sanitary fixtures and glass surfaces that can be used to provide “Easy to Clean” performance. This fluoropolymer will react with the surface to create a low surface energy coating that is not easily wetted with liquids. The treatment is stable and cannot be removed except by harsh cleaners or reagents, such as abrasive cleaners or a very strong base.

ECC-4000 coating is typically applied from a very diluted solution containing about 1.0% by weight of product, resulting in a coating thickness of 20 to 100 nm. ECC-4000 coating can be applied by spray application or dip coating. The treatment provides a hydrophobic surface that allows simple rinsing away of soils and sludge from the surface with no residual surface staining. The treated surface is durable, highly repellent to oils and water and does not change surface appearance.

Application ECC-4000 coating can be applied to ceramic surfaces at room temperature to provide low surface energy benefits.

The treated substrate will have:

- 1. Surface protection** ECC-4000 coating can be used for ceramic materials such as sinks, toilets, tiles (not floor tiles), showers tubs and other sanitary fixtures. It may also be used for indoor glass applications such as shower panels and mirrors.
- 2. Oil- and water-repellency** ECC-4000 coatings can be used to obtain repellency against any liquid having a surface tension greater than about 15 dynes/cm. This includes water, oils, ketones, and aromatic and aliphatic hydrocarbons.
- 3. Easy-to-clean properties** ECC 4000 coating is a built-in manufacturer applied treatment providing an easy to clean surface, resulting in consumer advantages such as:
 - stain resistance
 - easy removal of hard water deposits
 - no need for aggressive cleanersNote: “Easy-to-Clean” does not mean the surface is “self-cleaning.”
- 4. Enhanced lubricity** Soils and liquids tend to “slide off” surfaces treated with ECC-4000 coating, helping to prevent build-up and extend the time between cleanings.

**3M™ Easy Clean
Coating ECC-4000
Typical Physical
Properties**

Not for
specification
purposes

All values
determined at
25°C and 1
atmosphere
unless otherwise
specified

ECC-4000 coating can be described as a fluoropolymer solution.

Properties	ECC-4000 Coating
Appearance	Colorless to slightly yellow liquid
Specific gravity	0.92 kg/l
Flash point	12°C (54°F)
Type	non-ionic
Composition	10% fluoropolymer 60% alkoxysilane 30% ethanol

ECC-4000 coating can be diluted with alcohols, ketones, acetates or other solvents to give slightly hazy mixtures. ECC-4000 can be diluted with hydrofluoroethers (HFE) to give clear solutions. Instructions for proper product application can be found in the Application Guideline.

Typical Performance Data on Ceramic Materials	ECC-4000 Coating
Initial contact angles (water/hexadecane)	95°-110°/60°-65°
Contact angles after abrasion 50,000 cycles with WC-eend * cleaner 40 cycles with Cif**	80°-95°/45°-50° 70°-80°/40°-45°
Contact angles after exposure 24 hrs 18% HCl at 20°C	90°-95°/50°-55°

* "WC-eend cleaner" is a trademark of Bolton Group ** "Cif" is a trademark of Lever Fabergé

Typical Performance on Glass	ECC-4000 Coating
Initial contact angles*(water/hexadecane)	100°-120° / 60°-70°
Tilt angle (water)	15°-20°
Contact angles after abrasion 2000 cycles with brush/water 4000 cycles with brush/water	100°-110°/50°-60° 90°-100°/50°-60°
Contact angles after exposure 24 hrs 18% HCl at 20°C	90°-100°/50°-60°

**Storage and
Shelf Life**

It is recommended that ECC-4000 coating be stored in a closed bottle, away from direct sunlight, in a cool, dry place (temperatures between 10-25°C/50°-77°F). Avoid contact with moisture. Shelf life is 1 year from date of 3M manufacture.

**Product Safety
and Handling**

Before using this product, please read the Material Safety Data Sheet (available through your local 3M representative) and the precautionary information and directions for use on product packaging. Follow all applicable precautions and directions for use.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) 651 736 7123

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.



3M Specialty Materials

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3735-3



Easy Clean Coating ECC-5000

For Glazed Ceramic Wall Tiles

Introduction 3M™ Easy Clean Coating ECC-5000 is a clear, slightly yellow to amber colored concentrated product that can provide water, oil and stain repellency and easy-to-clean properties on glazed ceramic tiles. ECC-5000 coating is typically applied by spray application from a very diluted solution in water, containing about 0.1% to 0.5% by weight of product. As a result, it will give a virtually invisible coating with a thickness of about 20 to 100 nm.

The fluorochemical active ingredients will create a low surface energy coating that provides oleophobicity and hydrophobicity, and therefore is not easily wetted-out by liquids. The treatment will withstand moderate mechanical abrasion and cannot be easily removed except by harsh cleaners or reagents, such as a very strong base.

Application Waterborne dilutions of ECC-5000 coating can be applied to siliceous surfaces by various application methods, such as spraying, brushing, dipping or roller coating. A temperature cure of a few minutes at 80°-120°C (176-248°F) is needed to evaporate the water and optimize the performance of the treatment. Curing temperature can be as high as 250°C (482°F).

The product can be applied by spraying on hot tiles, immediately after the oven. Application on cold tiles, immediately after quality control, is also possible but must be followed by a heat cure by IR lamps or hot air.

The treated substrate will have:

- 1. Surface protection** ECC-5000 coating can be used for ceramic materials such as glazed wall tiles.
- 2. Oil- and water-repellency** ECC-5000 coating can be used to obtain repellency against any liquid having a surface tension greater than about 15 dynes/cm. This includes water, oils, ketones, aromatic and aliphatic hydrocarbons.
- 3. Easy-to-clean properties** ECC-5000 coating is a built-in, manufacturer applied treatment that provides easy-to-clean surfaces, resulting in consumer benefits such as:
 - resists stains, particularly oil based stains
 - easy to remove hard water deposits
 - no need for aggressive cleaners

Note: “Easy-to-Clean” does not mean the surface is “self-cleaning.”
- 4. Enhanced lubricity** Soils and liquids tend to “slide off” surfaces treated with ECC-5000 coating, helping to prevent build-up and extend the time between cleanings.

**3M™ Easy Clean
Coating ECC-5000
Typical Physical
Properties**

Not for specification
purposes

All values determined at
25°C and 1 atmosphere
unless otherwise
specified

ECC-5000 coating is a concentrated solution, containing a fluoropolymer, a fluoroacrylate copolymer, ethylacetate and isopropanol.

Properties	ECC-5000 Coating
Appearance	Slightly yellow to amber liquid
Specific gravity	about 1.0 kg/l
Flash point	12°C (54°)
Type	non-ionic
Typical analysis	40% fluoropolymer 10% fluoroacrylate copolymer 10% ethylacetate 40% isopropanol

ECC-5000 coating can be diluted with alcohols, ketones, acetates or other solvents to give slightly hazy mixtures. A clear solution is obtained when diluted in water. Instructions for proper product application can be found in the Application Guidelines.

Typical Performance Data	ECC-5000 Coating
Initial contact angles (water/hexadecane)	90°-100°/55°-65°
Contact angles after abrasion 40 cycles with Cif*	60°-70°/35°-45°
Contact angles after exposure 24 hrs 18% HCl at 20°C	80°-90°/45°-55°

* "Cif" is a trademark of Lever Fabergé

**Storage and
Shelf Life**

It is recommended that ECC-5000 coating be stored in a closed bottle, away from direct sunlight, in a cool, dry place (temperatures between 10-25°C/50°-77°F). Avoid contact with moisture. Shelf life is 1 year from date of manufacturing.

**Product Safety
and Handling**

Before using this product, please read the Material Safety Data Sheet (available through your local 3M representative) and the precautionary information and directions for use on product packaging. Follow all applicable precautions and directions for use.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) 651 736 7123

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.



3M Specialty Materials

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3736-1



Easy Clean Coating

Application Equipment

We suggest using the following spray equipment:

- Walther Pilot hand-held spray gun or equivalent
Type: Pilot MAXI HD, 1.5mm standard nozzle,
gravity feed cup
Alt nr: V 1161103153
- All materials of construction should resist acid-type liquids

Workplace Safety Recommendations

3M™ ECC Coatings should be applied in solvent spray cabins or in closed cabins with adequate ventilation.

Workers who may be exposed to the coatings and solvents during application should wear protective clothing, gloves and respiratory masks. For additional information, see the precautions and directions for use on the product packaging and the appropriate product Material Safety Data Sheet.

“Easy-to -Clean” Perception

The consumer’s perception of a surface being easy to clean will be strongest when the toilet or other sanitary fixture is treated inside (including the rim) and outside. This prevents hard water stains and other stains on inner and outer surfaces.

For glass shower doors, it is also important to treat the inside and outside. This is because ECC coatings protect not only against hard water deposits and soap scum, but also against oil-based stains and fingerprints.

Appearance of Tiles, Sanitary Ware and Glass

To ensure the best possible appearance of the treated substrate, it is important not to exceed the recommended add-on level of ECC coating. Excess coating, which will result in dull surfaces, can be removed within 30 minutes after coating with water or ethanol.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3742-9



Easy Clean Coating ECC-1000

For Ceramic Substrates

Substrate Preparation

Before treatment, the substrate should be cleaned (using aqueous detergents, acetone or ethanol) in order to remove dust and other contamination. This cleaning step is not necessary for freshly prepared ceramic.

Coating Solution Preparation

In a glass, stainless steel or plastic vessel, combine:

- 954 g ethanol (less than 0.1% water; can be denatured with alcohols, ethers or ketones)
- Add 30 g water
- Add 15 g of acetic acid
- Add 1 g of ECC-1000
- Mix well to obtain a slightly hazy solution.

Avoid contamination of any unused portion of ECC-1000 coating with water or acetic acid; if contaminated, the product will become useless. Use separate sampling utensils (e.g. syringes, pipettes, etc.) for each fluid.

This solution is only stable for a limited period of time (about 4–6 hours); therefore, it is recommended that you prepare only the amount of solution that can be used during that time.

Application

- Heat the part to 90–110°C (195–230°F). Depending on the size of the part to be treated and the capacity of the oven, this may take up to 1 hour.
- Spray the heated part uniformly with a very fine spray of the prepared solution at a pressure of about 2 bar (29 psi). Distance from spray pistol to the substrate should be approximately 10–20cm (4–8").
- The consumption of solution should be approximately 50–75 ml/m² (0.15–0.23 oz/ft²).
- Let the part rest until it has cooled to 40–50°C (104–122°F).
- Before the substrate has cooled down completely, gently remove the excess ECC-1000 coating with a soft cleaning paper.
- If the excess is difficult to remove, a mixture of ethanol and water may be used.

It may take up to 48 hours before final performance is achieved.

For additional information, contact your 3M technical service representative.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3738-7



Easy Clean Coating ECC-4000

For Ceramic and Glass Substrates

Substrate Preparation

Before treatment, the part should be cleaned (using aqueous detergents, acetone or ethanol) in order to remove dust and other contamination. This cleaning step is not necessary for freshly prepared parts.

The temperature of the ceramic substrate should preferably be 15–30°C (60–85°F).

Coating Solution Preparation

In a glass, stainless steel or plastic vessel, combine:

- 980 g ethanol (less than 0.1% water; can be denatured with alcohols, ethers and ketones)
- Add 10 g of ECC 4000, mix well
- Add 10 g of 37% HCl (12% normal) by weight
- Mix well to obtain a slightly hazy solution.

Avoid contamination of any unused portion of ECC-4000 coating with water or HCl; if contaminated, the product will become useless. Use separate sampling utensils (e.g., syringes, pipettes, etc.) for each fluid.

This solution is only stable for a limited period of time (4–6 hours); therefore, it is recommended that you prepare only the amount of solution that can be used during that time.

Application

- Spray the part uniformly with an air atomised micro droplet spray of the prepared solution at a pressure of about 2 bar (29 psi). Distance from spray pistol to substrate is approximately 10–20 cm (4–8").
- The consumption of solution should be approximately 30–40 g/m² (0.1–0.13 oz/ft²) for machine application and about 40–60 g/m² (0.13–0.2 oz/ft²) for manual application.
- Dry at room temperature for 10–30 minutes before handling or packaging.
- Check the aesthetics of the treated part. If excess coating is present, wipe it off with ethanol after about 10–30 minutes.

Although good performance is usually achieved after a few minutes, it may take up to 48 hours before final performance is achieved.

Note: The perception that the treated surface is “Easy-to-Clean” will be strongest when all exposed surfaces are treated both outside and inside.

For additional
information, contact
your 3M technical
service representative.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3740-3



Easy Clean Coating ECC-5000

For Glazed Ceramic Wall Tiles

Substrate Preparation

Before treatment the glazed tiles should be cleaned (using aqueous detergents, acetone or ethanol) in order to remove dust and other contamination. This cleaning step is not necessary for freshly prepared tiles.

The temperature of the tiles should be between 80–250°C (176–482°F), and preferably between 100–200°C (212–392°F).

Coating Solution Preparation

In a glass, stainless steel or plastic vessel, combine:

- 989 g water
- Add 10 g of 37% HCl (12% normal) by weight
- Add 1 g of ECC-5000
- Mix well to obtain a clear solution.

Avoid contamination of any unused portion of ECC-5000 coating with water or HCl; if contaminated, the product will become useless. Use separate sampling utensils (e.g., syringes, pipettes, etc.) for each fluid.

This solution is only stable for a limited period of time (about 4–6 hours); therefore, it is recommended that you prepare only the amount of solution that can be used during that time.

Application

- Spray the hot glazed tile uniformly with an air atomised micro droplet spray of the prepared solution at a pressure of about 2 bar (20 psi). Distance from spray pistol to the tile is approximately 10–20 cm (4–8").
- The add-on level should be approximately 40–50 g/m². (0.13–0.17 oz/ft²)
- Allow to cool to room temperature.
- It is important not to overspray the product because it can be difficult to remove the excess. If necessary, excess can be removed with soft cleaning paper or cloth just after treatment.

It may take up to 48 hours before final performance is achieved.

For additional information, contact your 3M technical service representative.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3741-1

Easy Clean Coatings

Measurement of static contact angle

Purpose

The contact angle is a measurement for the wetting or dewetting properties of a surface. Measurement of the contact angle therefore gives information on the hydro- and oleophobicity of a surface. High contact angles are typical for repellent substrates; low contact angles ($<20^\circ$) are typical for completely wettable surfaces. The specific contact angle on a substrate depends on the liquid used and the temperature. Fluorochemical coatings typically give contact angles with water of higher than 90° and with hexadecane higher than 50° .

Limitation

Contact angles below 20° are very difficult to measure; statistical error on measurements is about 5° .

Definition

The contact angle is the angle that the tangent line of the drop makes with the surface.

Principle

Surfaces with very low surface energy (such as those with fluorochemical treatments) have high contact angles.

Apparatus and materials

Static contact angles can be measured with a goniometer, such as an Olympus TGHM. DI water and hexadecane are the liquids typically used. Dynamic (advancing and receding) contact angles can be measured with commercially available equipment.

Test sample


A fluorochemical-treated substrate such as ceramic tile, glass, sanitary ware, porcelain, enamel, etc.

Test procedure

The substrate is mounted horizontally on the goniometer platform; a drop of liquid of about 5 microliters is put on the surface. While looking through the goniometer, a tangent line of the apparatus is moved in such a way that the line matches, as closely as possible, the curvature of the droplet. The tangent line dissects a scale from $0-180^\circ$. The intersection gives the contact angle in degrees. Dynamic contact angle measuring devices do these operations automatically and provide the data (contact angle, surface energy, etc.) electronically.

Evaluation and rating

Contact angle in degrees is read on the scale.



Abrasion test with water

Purpose	To test the mechanical abrasion resistance of a fluorochemical coating.
Limitation	The equipment used in the abrasion with water test is a linear abrader; curved surfaces cannot be tested using this technique.
Definition	The treated substrate undergoes mechanical abrasion by moving a water-soaked sponge that is mounted on a metal holder. A number of cycles are made during which the sponge moves linearly and horizontally over the surface. Water is automatically added.
Apparatus and materials	Erichsen Washability and Scrubbing Tester Model 494, equipped with a microdose pump and a metal holder; a sponge or a Scotch-Brite™ High Performance Wipe; and tap water. The metal holder weighs 400-450 grams.
Test sample	Fluorochemical-treated ceramic, glass, enamel or tile.
Test procedure	Flat substrate is fixed in a frame of the Erichsen machine; a water-saturated sponge is applied to the substrate and 4,000 cleaning cycles are performed. Water is continuously dripped onto the surface. After 24 hours, the contact angles with DI water and hexadecane are measured.
Evaluation and Rating	Contact angles after the abrasion test are measured.

Abrasion test with cleaner

Purpose	To test the mechanical abrasion resistance of a fluorochemical coating.
Limitation	The equipment used in the abrasion test with cleaner is a linear abrader; curved surfaces cannot be tested using this technique.
Definition	The treated substrate undergoes mechanical abrasion by a moving, detergent-soaked brush or wipe, mounted on a metal holder. A number of cycles are made during which the brush moves linearly and horizontally over the surface.
Apparatus and materials	Erichsen Washability and Scrubbing Tester Model 494, equipped with a microdose pump and a metal holder; a DIN brush or a Scotch-Brite™ High Performance Wipe. An abrasive cleaner (eg. Cif) and a mild detergent (eg. WC-eend) can be used. The metal holder weighs 400-450 grams.
Test sample	Fluorochemical-treated ceramic, glass, enamel or tile.
Test procedure	Flat treated substrate is fixed in a frame of the Erichsen machine; 1) about 5 ml of abrasive cleaner are applied to the substrate and 40 cleaning cycles are completed; the detergent is carefully washed off with water. After 24 hours the contact angles are measured using DI water and hexadecane. 2) about 5 ml of mild detergent are applied to the substrate and 50,000 cycles are completed; every 1,000 cycles, 5 ml additional detergent is re-applied; after the cleaning cycles, the detergent is carefully washed off with water.
Evaluation and Rating	24 hours after the test procedure has been completed, contact angles are measured, using water and hexadecane.

Exposure to HCl

Purpose	To test the chemical resistance of a treatment.
Limitation	The substrates must be stable to strong acids. The chemicals must be used in a liquid, diluted form.
Definition	A treatment is stable to chemicals if it keeps its repellent characteristics for a specific amount of time when exposed to chemicals of a certain nature and concentration.
Principle	Treated substrate is brought in contact with HCl at room temperature.
Apparatus and materials	Metal cylinders 85 mm in diameter and 10 mm high; structural adhesive 3M™ Scotchweld™ Epoxy Adhesive DP-110; glass petri dishes; aqueous solution of 18% HCl.
Test sample	Treated ceramics, glass, enamel and tiles.
Test procedure	A cylinder made out of stainless steel pipe with an inner diameter of 85 mm and a length of 10 mm is glued to the treated substrate with structural adhesive and allowed to cure for 1 hour. The substrate is then placed horizontally. 10 ml of 18% HCl is then poured in the ring. The ring is covered on top by the petri dish to avoid evaporation. After 24 hours the test liquid, metal ring and adhesive are removed. The treated substrate is thoroughly rinsed with water and allowed to dry at room temperature for 24 hours.
Evaluation and Rating	24 hours after the test has been completed, contact angles are measured, using DI water and hexadecane.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3730-4



Easy Clean Coating ECC-1000 ECC-4000

Ceramic Sanitary Ware

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90°/>55°
Contact angles after abrasion with Erichsen cleaning device-DIN 53788 50.000 cycles WC-eend (Johnson)	Abrasion Test w/Cleaner	>85°/>45°
40 cycles CIF (Lever)	Abrasion Test w/Cleaner	>70°/>40°
Chemical Resistance 24 hrs 18% HCl at 20°C	Exposure to HCl	>90°/>50°

Glass for Shower Cabins

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90°/>55°
Contact angles after abrasion with Erichsen cleaning device-DIN 53788 4.000 cycles water-sponge	Abrasion Test w/Water	>85°/>45°
Chemical Resistance 24 hrs 18% HCl at 20°C	Exposure to HCl	>85°/>50°

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3732-0



Easy Clean Coating ECC-1000 ECC-4000

Ceramic Sanitary Ware

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90°/>55°
Contact angles after abrasion with Erichsen cleaning device-DIN 53788 50.000 cycles WC-eend (Johnson)	Abrasion Test w/Cleaner	>85°/>45°
40 cycles CIF (Lever)	Abrasion Test w/Cleaner	>70°/>40°
Chemical Resistance 24 hrs 18% HCl at 20°C	Exposure to HCl	>90°/>50°

Glass for Shower Cabins

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90°/>55°
Contact angles after abrasion with Erichsen cleaning device-DIN 53788 4.000 cycles water-sponge	Abrasion Test w/Water	>85°/>45°
Chemical Resistance 24 hrs 18% HCl at 20°C	Exposure to HCl	>85°/>50°

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3732-0



Easy Clean Coating ECC-5000

Glazed Wall Tiles

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90°/>55°
Contact angles after abrasion with Erichsen cleaning device-DIN 53788		
5000 cycles with Mr Propre	Abrasion Test w/Cleaner	>70°/>40°
40 cycles with CIF (Lever)	Abrasion Test w/Cleaner	>60°/>30°
Chemical Resistance 24 hrs 18% HCl at 20°C	Exposure to HCl	>80°/>50°

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M is a trademark of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3733-8



Scotchgard™ Protector

Performance Specifications
for Scotchgard
Brand Licensed Applications

For Ceramic Sanitary Ware and Shower Glass

Introduction

The Scotchgard brand can only be used by businesses that have a current Trademark License for the Scotchgard brand on file with 3M. Use of the Scotchgard brand also requires that treated substrates meet the Qualification and Performance Specifications for their specified use.

Performance testing and quality monitoring to ensure that the brand specifications are met are primarily the responsibility of the licensee. Although the Trademark License provides for corroborative testing by 3M or its authorized representatives, this testing is meant only to supplement the performance testing of the licensee; it is not a substitute for such testing.

Product Used

ECC-1000 and ECC-4000 coatings are intended for use on glazed sanitary fixtures (toilets, sinks, etc.) manufactured from ceramic substrates and interior glass surfaces (showers, mirrors, etc.). They are not intended for use on tile. This specification requires that all glazed surfaces where staining or soil can be observed must be treated, including:

- Two-piece toilets – All surfaces of the bowl, inside and outside
- One-piece toilets – All glazed surfaces, excluding reservoir cover
- Drop-in sinks – All glazed surfaces
- Pedestal sinks – All glazed surfaces on the sink; treatment of the pedestal is not required.
- Cantilevered and other sinks – All glazed surfaces
- Ceramic faucet taps, shower heads and other ceramic fixtures – All glazed surfaces.
- Shower glass — Inside and outside.

Refer to the Application Guidelines specific to these products for methods of substrate preparation and treatment application.

Performance Specifications for Ceramic Sanitary Ware

The minimum application level of 40 g/m² (0.13 oz/ft²) of 0.1% treating solution of ECC-1000 or 1.0% treating solution of ECC-4000 must be sufficient to meet the following performance specification:

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90° / >55°
Contact Angles after Abrasion with Erichsen Cleaning Device – DIN 53788 40 Cycles CIF (Lever)	Abrasion Test with Cleaner	>70° / >40°
Chemical Resistance 24 hrs 18% HCl @ 20°C	Exposure to HCl	>90° / >50°

Table of Contents

Performance Specifications for Glass

The minimum application level of 40 g/m² (0.13 oz/ft²) of 0.1% treating solution of ECC-1000 or 1.0% treating solution of ECC-4000 must be sufficient to meet the following performance specification:

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90°/>55°
Contact angles after abrasion with Erichsen cleaning device -DIN 53788 4.000 cycles water-sponge	Abrasion Test w/Water	>85°/>45°
Chemical Resistance 24 hrs 18% HCl at 20°C	Exposure to HCl	>85°/>50°

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

Asia Pacific and Latin America

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.



3M Specialty Materials

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M and Scotchgard are trademarks of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3749-4



Scotchgard™ Protector

Performance Specifications
for Scotchgard
Brand Licensed Applications

For Ceramic Wall Tile

Introduction

The Scotchgard brand can only be used by businesses that have a current Trademark License for the Scotchgard brand on file with 3M. Use of the Scotchgard brand also requires that treated substrates meet the Qualification and Performance Specifications for their specified use.

Performance testing and quality monitoring to ensure that the brand specifications are met are primarily the responsibility of the licensee. Although the Trademark License provides for corroborative testing by 3M or its authorized representatives, this testing is meant only to supplement the performance testing of the licensee; it is not a substitute for such testing.

Product Used

ECC-5000 coating is intended for use on glazed ceramic wall tiles only.

Refer to the Application Guidelines specific to this product for methods of substrate preparation and treatment application.

Performance Specifications

The minimum application level of 40 g/m² (0.13 oz/ft²) of 0.1% treating solution must be sufficient to meet the following performance specification:

Test	3M Test Method	Contact Angle (water/hexadecane) Minimum Specs
Initial Contact Angles	Measurement of Static Contact Angle	>90° / >55°
Contact Angles after Abrasion with Erichsen Cleaning Device – DIN 53788 40 Cycles CIF (Lever)	Abrasion Test with Cleaner	>60° / >35°
Chemical Resistance 24 hrs 18% HCl @ 20°C	Exposure to HCl	>80° / >50°

These tests shall be performed at the start of every run, and upon completion of every 100 pieces. Test samples shall be made available to 3M or its authorized representatives, as described in the document, “Quality Monitoring Requirements.”

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M and Scotchgard are trademarks of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3748-6



Easy Clean Coatings

Use of the Scotchgard™ brand

The Scotchgard brand can only be used by businesses that have a current Trademark License for the Scotchgard brand on file with 3M. Use of the Scotchgard brand also requires that treated substrates meet the Qualification and Performance Specifications for their specified use.

Performance testing and quality monitoring to ensure that the brand specifications are met are primarily the responsibility of the licensee. The Trademark License provides for corroborative testing by 3M or its authorized representatives. This testing is meant only to supplement the performance testing of the licensee; it is not a substitute for such testing.

Quality assurance testing procedures

Production samples of substrates treated with a 3M™ Easy Clean Coating material must be tested in accordance with prescribed 3M test methods and frequency to ensure continual quality of the treated finish.

A profile of the typical end-users of the substrates will determine which performance tests are required. These tests include: oil and water repellency, chemical resistance and abrasion resistance. Refer to the “Qualification and Performance Specification” and “Test Methods” documents for the appropriate tests and test results required to pass a particular performance specification.

It is required that accurate records for each production lot of substrates and each test value be kept as a record for both future application formulations and problem solving.

Sample submission procedure

- 1) Not less than every thirty (30) days, representative samples and test results of treated materials must be sent to 3M or its authorized representative who will do the corroborative performance monitoring testing.
- 2) Results of the Performance Monitoring testing will be summarized monthly and a copy will be sent by 3M to the manufacturer submitting the samples. If performance monitoring is done by a 3M authorized representative, a copy will also be sent to 3M.

United States

3M Specialty Materials
3M Center, Building 223-6S-04
St. Paul, MN 55144-1000
800 541 6752
800 810 8514 (Fax)

Europe

3M Specialty Materials
3M Belgium N. V.
Haven 1005, Canadastraat 11
B-2070 Zwijndrecht
32 3 250 7521

Canada

3M Canada Company
Specialty Materials
P.O. Box 5757
London, Ontario
N6A 4T1
800 364 3477

Japan

Sumitomo 3M Limited
33-1, Tamagawadai 2-chome
Setagaya-ku, Tokyo
158-8583 Japan
813 3709 8250

**Asia Pacific and
Latin America**

Call (U.S.) **651 736 7123**

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

**3M Specialty Materials**

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/specialtymaterials

3M and Scotchgard are trademarks of 3M.
Used under license by 3M subsidiaries and affiliates.

Issued: 4/04

© 2004 3M

4752(HB)
98-0212-3743-7